

CERTIFICATE OF MAILING BY FIRST CLASS MAIL (37 CFR 1.8)

Applicant(s): Yasushi AKIYAMA et al.

Docket No.

2002JP311

Serial No.

10/519,242

Filing Date

December 22, 2004

Examiner

WU, Ives J.

Group Art Unit

1713

Invention: **COMPOSITION FOR ANTIREFLECTIVE COATING AND METHOD FOR FORMING SAME**

SEP 14 2005

I hereby certify that this English Language abstract of JP 09-236915 - 2 Pages

(Identify type of correspondence)

is being deposited with the United States Postal Service as first class mail in an envelope addressed to: The

Commissioner of Patents and Trademarks, Washington, D.C. 20231-0001 on

September 14, 2005

(Date)

MARIA T. SANCHEZ

(Typed or Printed Name of Person Mailing Correspondence)

Maria T. Sanchez
(Signature of Person Mailing Correspondence)

Note: Each paper must have its own certificate of mailing.

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-236915

(43)Date of publication of application : 09.09.1997

(51)Int.Cl. G03F 7/004

G03F 7/11

H01L 21/027

(21)Application number : 08-347528 (71)Applicant : MITSUBISHI CHEM CORP

(22)Date of filing : 26.12.1996 (72)Inventor : NISHI MINEO

TERAMOTO MASASHI

(30)Priority

Priority number : 07340612

Priority date : 27.12.1995

Priority country : JP

(54) ANTIREFLECTION COMPOSITION AND RESIST PATTERN FORMING METHOD

(57)Abstract:

PROBLEM TO BE SOLVED: To suppress mixing with a photoresist, to ensure satisfactory step coverage even with a thin film thickness, to prevent dissolution at the time of developing a photoresist film, to attain high absorbance even when the amt. of a light absorber added is small and to ensure satisfactory dry etching resistance by incorporating water and PVA and imparting acidity of a specified pH or below.

SOLUTION: This compsn. contains water and PVA and has \leq pH4. The PVA resin is produced by hydrolyzing polyvinyl acetate and converting acetyl groups in the polyvinyl acetate into hydroxyl groups. The mol% of such hydroxyl groups means the degree of saponification and PVA resin having 70-99% degree of saponification is preferably used. In the case of <70% degree of saponification, developer resistance is deteriorated at the time of development and mixing is liable to occur at the time of forming a photoresist film. In the case of >99%, the shelf stability of this compsn. is deteriorated.

LEGAL STATUS [Date of request for examination] 11.11.2003

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or
application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office